

LNS 164

CLASSIFICATION

AWS A5.23/A5.23M : EF3
ISO 14171-A : S3 Ni1Mo

GENERAL DESCRIPTION

Nickel and Molybdenum alloy wire to reach both high yield/ tensile properties and good impact toughness at low temperatures
Optimum results obtained with the multipass technique
Meet NACE requirement

APPROVALS

TÜV

P230	X
P240	X

CHEMICAL COMPOSITION (W%), TYPICAL, WIRE

C	Mn	Si	Ni	Mo
0.10	1.75	0.10	0.9	0.5

PACKAGING AND AVAILABLE SIZES

Diameter (mm)	2.4	3.2	4.0	4.8
Unit : 25 kg stein basket B415	X	X	X	X
25 kg stein basket B415 + VCI	X	X	X	
100 kg stein basket B785		X	X	
300 kg wooden reel			X	
350 kg Speed Feed® Drum	X		X	
400 kg Speed Feed® Drum		X	X	

LNS 164 rev. EN 02

Liability: All information in this data sheet is based on the best available knowledge, is subject to change without notice and can only be considered as suitable for general guidance. Fumes: Consult information on Welding Safety Sheet, available upon request